



Product Information

Surfactants

EMULPON CO-360

Ethoxylated Castor Oil

Specification

	Limits	Method
Appearance (25°C)	Creamy paste @ 25C max	*
Cloud point	74 - 80 C	*
Moisture	0.2 % max	*
pH, 5% in 25% IPA	6.5 - 7.5	*

*Methods of analysis can be received upon request.

Typical data

Chemical and physical data

Appearance	Viscous liquid Light yellow @25 C
Density	1.06 g/cm ³ @ 25C
Flash point	>94 C
HLB value according to Griffin	13.4
Hydroxyl number	63 - 69
Melting point	30-34 C
Odor	Fatty
Percent Volatiles	0
pH	6-8
Specific Gravity	1.06 @ 25°C
Surface tension according to Du Noüy, 25°C, 0.1% DIN 53 914	38.6 mN/m

Typical values

Appearance	Viscous liquid Light yellow @25 C
Density	1.06 g/cm ³ @ 25C
Flash point	>94 C
HLB value according to Griffin	13.4
Hydroxyl number	63 - 69
Melting point	30-34 C
Odor	Fatty
Percent Volatiles	0
pH	6-8
Specific Gravity	1.06 @ 25°C
Surface tension according to Du Noüy, 25°C, 0.1% DIN 53 914	38.6 mN/m

Solubility

Water	Soluble
-------	---------

The specifications and properties listed above are intended for products manufactured in USA.

Further Information

For further information, technical service and samples, please contact our nearest Akzo Nobel Sales office or agent/distributor.